

PRODUCT DATA SHEET

Sika®-101h

Ready to use crystallizing waterproofing system and moisture seal for mortar and concrete

DESCRIPTION

Sika®-101h is a ready to use cement based powder capillary waterproofing system for concrete and mortar to prevent water infiltration or seepage of water in the area of low pressure of concrete structure or any cementitious substrate.

USES

Sika®-101h forms slurry consistency when mixed with water. When it is applied to the concrete substrate it forms insoluble crystals inside water bearing capillaries and seal against further seepage of water. Sika®-101h blocks the pores in concrete structures such as :

- Basement
- Reservoirs
- Sewage water and effluent treatment plant
- Tunnel and underground subways
- Foundations
- Swimming pools
- Underground parking structures
- Water tanks

CHARACTERISTICS / ADVANTAGES

It provides the following beneficial properties in post applied waterproofing :

- Easy to apply
- Can be used for positive and negative side waterproofing
- Helps in faster construction schedule
- Can seal hairline cracks
- Becomes an integral and homogenous part of the structure
- Allows the substrate to breath
- No added chloride
- Non-toxic

PRODUCT INFORMATION

Packaging	30 kg, HDPE Bag
Appearance / Colour	Cementitious Grey granular powder
Shelf Life	6 months from date of production if stored properly in undamaged and unopened original sealed packaging in dry and cool conditions.
Storage Conditions	Material must be stored in dry and cool place.
Density	~ 1.3 kg/l (Bulk Density)

TECHNICAL INFORMATION

Permeability to Water Vapour	Impermeable at 3kg/cm ²	According to IS 2645 & ASTM C 1306-05a
Water Penetration under Pressure	Penetrates into the concrete upto complete capillary depth where water can penetrate	

APPLICATION INFORMATION

Mixing Ratio	Water : Powder 0.28 - 0.30 by weight
Consumption	~ 1.2 kg/m ² per coat. Two coats always recommended. ~1.8kg/m ² as a dry shake ~0.8% by weight of cement as an additive to concrete
Consistency	Brushable consistency.
Initial Set Time	Workable time of the System is ~ 40 min at 30 °C

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

Sika®-101h must be prevented from drying out too rapidly. The freshly applied surface must be protected from rain, strong winds and direct sunshine. Keep moist using damp hessian and covering with polythene sheet for first 3-4 days after application. Protect slurry in pedestrian areas overlaying with 1:3 cement sand screed.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete surface must be clean, sound, level and uncontaminated by oil or grease. Remove cement laitance, formwork-traces and loosely adhering particles by mechanical means. Area of honeycomb concrete and other surface imperfections must be repaired with cement sand mortar. De bonding render must be removed. Wet surface until saturated.

MIXING

Add powder to given amount of water and stir with low speed mixer for 5 minutes until a lump free smooth brushable consistency is achieved.

APPLICATION

During application of Sika®-101h add a liquid applied polymer modified flexible coating system with crystallisation properties. The following procedure shall be adapted for application.

For the 1st Coat of Sika®-101h is mixed with water to produce crystalline slurry and to be coated with the help of a brush or roller. When the first coat is in tacky condition Sika®-101h is mixed with water to produce crystalline slurry and to be coated with the help of a brush or roller.

Sika®-101h also has multiple application as

- Dry shake over freshly laid PCC (no waiting time required after PCC for waterproofing)
- As a waterproofing additive to the concrete

CLEANING OF TOOLS

Clean all tools and application equipment with clean water immediately after use. Hardened / cured material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's cur-

PRODUCT DATA SHEET

Sika®-101h

May 2021, Version 01.01

020701010010000208

rent knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika Pakistan (Pvt.) Limited

141-CCA Phase IV, DHA
Lahore Punjab 54792
Pakistan
phone: +92 42 3569 4266 - 67
fax: +92 42 3569 4268
<http://pak.sika.com/>

PRODUCT DATA SHEET

Sika®-101h
May 2021, Version 01.01
020701010010000208

