

MasterFlow[®] 932 AN

Pure epoxy (1:1) resin based high performance anchoring grout

DESCRIPTION

MasterFlow 932 AN is a two-component (1:1) pure epoxy resin based high performance anchoring grout for use in cracked and uncracked concrete under normal as well as seismic conditions (seismic category C1). Designed for most demanding structural applications and rebar connections, **MasterFlow 932 AN** offers high load-bearing capacity.

TYPICAL APPLICATIONS

- Structural applications in cracked and uncracked concrete applications in seismic zones (C1)
- Façades
- Post installed rebar connections
- Crash barriers
- Structural steel

APPROVALS & TESTS

- ETA according ETAG 001 Part 1 & 5 Option 1 for anchoring of threaded bars into cracked & uncracked concrete application in seismic zones (C1)
- ETA according to TR023 for post-installed rebar connections
- Tested according to LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)
- Fire resistance F240 for reinforcing bars
- A+ as per French VOC Regulation
- ICC-ES Evaluation report for use in cracked and uncracked concrete

ADVANTAGES



- Fixings close to free edges
- Fire tested
- Versatile
- Anchoring without expansion pressure
- High load capacities
- Extended gel/open time
- Suitable for dry and wet holes

PACKAGING

MasterFlow 932 AN is available in boxes of 12 side-by-side cartridges of 650 ml to be used with AG600B application tool.

APPLICATION GUIDELINES

Please refer to the method statement or contact Master Builders Solutions Technical Services department.



MasterFlow[®] 932 AN

WORKING & LOADING TIMES

Resin cartridge Temperature	T Work	Base Material	T Load
+10 to +15°C	20 mins	+5 to +10°C	24 hrs
		+10 to +15°C	12 hrs
+15 to +20°C	15 mins	+15 to +20°C	8 hrs
+20 to +25°C	11 mins	+20 to +25°C	7 hrs
+25 to +30°C	8 mins	+25 to +30°C	6 hrs
+30 to +35°C	6 mins	+30 to +35°C	5 hrs
+35 to +40°C	4 mins	+35 to +40°C	4 hrs
+40°C	3 mins	+40°C	3 hrs

PHYSICAL PROPERTIES

Property		Unit	Value	Test Standard
Density		kg/L	1.5	ASTM D 1875 @ +20°C / +72°F
Compressive Strength	24 hours	N/mm ²	75	ASTM D 695 @ +20°C / +72°F
	7 days	N/mm ²	95	
Tensile Strength	24 hours	N/mm ²	18	ASTM D 638 @ +20°C / +72°F
	7 days	N/mm ²	23	
Elongation at Break	24 hours	%	6.6	ASTM D 638 @ +20°C / +72°F
	7 days		5.9	
Tensile Modulus	24 hours	GN/m ²	5.7	ASTM D 638 @ +20°C / +72°F
	7 days	GN/m ²	5.5	
Flexural Strength	24 hours	N/mm ²	45	ASTM D 790 @ +20°C / +72°F
HDT	7 days	°C	49	ASTM D 648 @ +20°C / +72°F
VOC		g/L	3	ASTM D 2369

THEORETICAL NUMBER OF FIXINGS PER CARTRIDGE

Applies to installations in solid substrates only

Cartridge Volume	h _{ef}	Ø8	Ø10	Ø12	Ø16	Ø20	Ø24	Ø27	Ø30
		Drilling Ø 10mm	Drilling Ø 12mm	Drilling Ø 14mm	Drilling Ø 18mm	Drilling Ø 22mm	Drilling Ø 26mm	Drilling Ø 30mm	Drilling Ø 35mm
650 ml side by side	8d	240	147	98	52	31	19	12	6
	10d	192	118	78	42	24	15	9	5
	12d	160	98	65	35	20	13	8	4
	20d	96	59	39	21	12	7	4	2

Note: Jobsite/contractor installations usually result in more resin being injected than the theoretical requirement resulting in lower number of fixings per cartridge. The reduction to the number of fixings per cartridge in practice is greater for smaller diameter holes and shallower embedment depths.

MasterFlow[®] 932 AN

MasterFlow 932 AN with REINFORCING BARS (ANCHOR THEORY)

INSTALLATION PARAMETERS

Diameter of rebar (mm)	10	12	16	20	25	32
Drilled hole diameter (mm)	14	16	20	25	32	40

DESIGN RESISTANCE

Rebar size			Ø10	Ø12	Ø16	Ø20	Ø25	Ø32
Effective embedment depth h_{ef} [mm]			90	110	125	170	250	300
non-cracked concrete temperature range (-40°C / +40°C)								
tension	C20/25	$N_{Rd,p}$ [kN]	18.85	23.70	38.90	66.12	121.55	186.70
	C50/60	$N_{Rd,p}$ [kN]	21.49	27.01	44.34	75.38	138.57	212.84
shear	C20/25	$N_{Rd,s}$ [kN]	9.33	14.67	20.67	57.33	90.00	147.33
cracked concrete temperature range (-40°C / +40°C)								
tension	C20/25	$N_{Rd,p}$ [kN]	14.14	17.77	20.94	35.60	46.75	71.81
	C50/60	$N_{Rd,p}$ [kN]	15.41	19.37	22.83	38.81	50.96	78.27
shear	C20/25	$N_{Rd,s}$ [kN]	9.33	14.67	20.67	57.33	90.00	147.33

RECOMMENDED RESISTANCE

Rebar size			Ø10	Ø12	Ø16	Ø20	Ø25	Ø32
Effective embedment depth h_{ef} [mm]			90	110	125	170	250	300
non-cracked concrete temperature range (-40°C / +40°C)								
tension	C20/25	$N_{Rec,p}$ [kN]	13.46	16.93	27.78	47.23	86.82	133.36
	C50/60	$N_{Rec,p}$ [kN]	15.35	19.30	31.67	53.84	98.98	152.03
shear	C20/25	$N_{Rec,s}$ [kN]	6.67	10.48	14.76	40.95	64.29	105.24
cracked concrete temperature range (-40°C / +40°C)								
tension	C20/25	$N_{Rec,p}$ [kN]	10.10	12.69	14.96	25.43	33.39	51.29
	C50/60	$N_{Rec,p}$ [kN]	11.01	13.84	16.31	27.72	36.40	55.91
shear	C20/25	$N_{Rec,s}$ [kN]	6.67	10.48	14.76	40.95	64.29	105.24

$f_{yk} = 500 \text{ N/mm}^2$

Partial safety factor $\gamma_{1.4}$

For resistance values in higher temperatures, please contact Master Builders Solutions Technical Services.

All the above resistance values are considering combined pull out and concrete cone failure in tension and steel failure in shear

MasterFlow[®] 932 AN

STORAGE AND SHELF LIFE

Cartridges should be stored in their original packaging, the correct way up and in cool dry conditions (+10°C to +25°C) out of direct sunlight. When stored correctly, the shelf life will be for 12 months from the date of manufacture.

QUALITY AND CARE

All products originating from Master Builders Solutions Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC Group in many countries.

MBS_CC-UAE/FI_932AN_v10/01_19/v11/09_19

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions
Construction Chemicals LLC
P.O. Box 37127, Dubai, UAE
Tel: +971 4 8090800
www.master-builders-solutions.com/en-ae

Disclaimer: the LRQA mark relates to certified management system and not to the product mentioned on this datasheet



A brand of
MBCC GROUP